

# Rotary Kiln Bauxite 86

## CHARACTERISTICS

| Chemical Characteristics       | Specifications (%) |
|--------------------------------|--------------------|
| Al <sub>2</sub> O <sub>3</sub> | Min 86             |
| TiO <sub>2</sub>               | Max 4              |
| Fe <sub>2</sub> O <sub>3</sub> | Max 2              |
| Na <sub>2</sub> O              | Max 0.70           |
| CaO                            |                    |
| MgO                            |                    |
| K <sub>2</sub> O               |                    |

| Physical Characteristics | Specifications                |
|--------------------------|-------------------------------|
| Bulk Density             | Min 3.15 (g/cm <sup>3</sup> ) |

Size: 0-0.1mm,0-1mm, 1-3mm, 3-5mm

Packing: 1 MT,1.25 MT big bag

Note: The data is based on average results, so a slight variation in the values be observed.



**ARSHIA ORANG Co.**

No.17, 5th St., North Falamak Ave., Shahrak Gharb

Zip: 1467885484, Tehran – Iran

Tel.: +98 21 57618

Fax: +98 21 88075715

E-mail: info @ arshiaorang.com