CHRYSO[®]Fluid IR HP2 CHRYSO[®]Fluid IR HP2



Superplasticizer – High Range Water Reducer

Features

Technical Datasheet

CHRYSO®Fluid IR HP2 is a second generation superplasticizer – high range water reducer, based on modified polycarboxylate.

CHRYSO®Fluid IR HP2 is especially recommended for concrete requiring high early age and long term strengths, whilst maintaining the workability.

CHRYSO®Fluid IR HP2 enables the production of concrete with very low W/C ratios.

CHRYSO®Fluid IR HP2 enables the production of self-leveling concrete.

Benefits

- Enhances the workability retention of concrete in hot climates.
- High water reduction ability.

• The dispersion properties of CHRYSO®Fluid IR HP2 allow the user to optimise the cement content when a specified mechanical strength is required.

Areas of Application

CHRYSO®Fluid IR HP2 is recommended for all concrete mixes where water content, improved cementitious material performance, high workability retention and very high strengths characteristics are desirable.

- 1. All types of cement
- 2. Heavy prefabrication
- 3. High performance concrete, ultra high performance concrete
- 4. Pre-stressed concrete
- 5. Ready-mix concrete
- 6. Concrete of humid, plastic or fluid consistency
- 7. Normal or high flowable concrete
- 8. High strength concrete with high workability retention
- 9. Compatible with Micro silica, GGBS and Fly Ash.





CHRYSO[®]Fluid IR HP2 CHRYSO[®]Fluid IR HP2

Description:

Characteristics:

CHRYSO®Fluid IR HP2 is a chemically stable liquid.

1.Nature : liquid 2.Colour : Pale Yellow 3.Density : 1.06 + 0.020

3.Density : 1.06 ± 0.020 4.pH : 6.5 ± 2 5.Cl⁻ ion content : nil to EN 934 and BS 5075 6.Na₂O equiv. : ≤ 1.0 %

CHRYSO®Fluid IR HP2 does not contain any purposely added calcium chloride or other chloride based components. It will not promote or contribute to corrosion of reinforcing steel in concrete.

Packaging:

– Bulk – IBC: 1000 L – Drums : 215 L – Drums: 60 L

Standard specifications:

Conforms to ASTM C 494 Type A, F and G and BS EN 934-2

Directions for use:

Dosage

between 0.3 and 2.5 litre per 100 kg of total cementitious material. A 1.0 % dosage of the product to the weight of cement is commonly used.

CHRYSO®Fluid IR HP2 can be added to the water before mixing the concrete. However, it can be added to the concrete after mixing.

Dosage rates of **CHRYSO®Fluid 1R HP2** are dependent upon desired concrete performance characteristics and variables including cement quantity and chemistry, concrete temperature and curing conditions.

Because local job conditions vary, please contact your local CHRYSO sales representative for further assistance if using outside recommended dosage ranges.

Compatibility:

CHRYSO®Fluid IR HP2 is compatible with all types of cement, class C and F fly ash, slag, microsilica, calcium chloride, fibers and approved air entraining admixtures.

Precaution:

• Store away from frost. Use CHRYSO®Fluid IR HP2 at a temperature superior to 0°C.

• Should the product freeze, its properties can be recovered after thawing and agitating thoroughly.

- This product must be stored in plastic containers, but not in PVC.
- Shelf life: 12 months.

Safety:

CHRYSO®Fluid IR HP2 is not considered dangerous to handle. Please refer to the material safety data sheet for additional information.

About CHRYSO:

Worldwide leader for cement and concrete additives for over 70 years, **CHRYSO** has been designing, producing, specifying and delivering its added-value solutions to the construction professionals with outstanding innovation and quality service. As a result, **CHRYSO**'s brand and products have been associated with the most prestigious and demanding construction projects over the globe.

Manufactured under License by,



No.17, 5th St., North Falamak Ave., Shahrak Gharb Tel: +98 21 88370130 up to 4 - Fax: +98 21 88075715 Zip1467885484 Tehran, Iran - E-mail: info@arshiaorang.com

The information contained in this document is given to the best of our knowledge and is the result of extensive and controlled testing. However, it cannot under any circumstances be considered as a warranty involving our liability in the case of misuse. Tests should be conducted before the product is used to ensure that the methods and conditions of use of the product are satisfactory. Our specialists remain at the disposal of customers if they require help with the application of the product for their specific needs.